

Amendments to the Specification:

Please replace the paragraph beginning at page 11, line 11 with the following amended paragraph:

In the step of backing (S5), the dyed carpet is ~~beek~~ back coated with latex so that piles do not come off, followed by being adhered to a second foundation cloth such as jute and polypropylene foundation cloth, and PVC or SBS (styrene butadiene styrene) is used as an auxiliary mat, i.e., a backing reinforcement. Latex comprises solids of 80%, in detail, base latex of 30 to 50%,  $\text{CaCO}_3$  of 50 to 70%, dispersing agent, and viscosity enhancing agent. To increase a reserve effect, small amount of  $\text{Al}_2\text{O}_3$ , or  $\text{Al}_2\text{OH}_3$  may be added to latex.

Please replace the abstract at page 24 with the following amended abstract:

Disclosed is a method for preparing a poly(trimethylene terephthalate) carpet, in which the poly(trimethylene terephthalate) carpet is prepared from poly(trimethylene terephthalate) yarns through the post-processes comprising cabling, heat setting, tufting, dyeing, ~~beeking~~ backing, and shearing. The poly(trimethylene terephthalate) yarns have advantages of improved quality, functionality, and workability by optimizing operating conditions of the steps.